

Product Information

Enduro Protect, EN40-230

Physical Properties*

DENSITY	39.0 to 42.0 kg/m ³	I.F.D. HARDNESS RANGE (NEWTONS)
TEAR RESISTANCE	180N/m Minimum	IF 40% Minimum 210N
TENSILE STRENGTH	100kPa Minimum	IF 40% Maximum 250N
ELONGATION	90% Minimum	IF 25% RECOVERY 75% Minimum
RESILIENCE	45% Minimum	INDENTATION
COMPRESSION SET (75%)	8% Maximum	(SAG) FACTOR 2.3 Minimum

* When tested internally in accordance with the test methods listed in Australian Standard AS2282.0

Available Colours

Orange

Tested to the following Flammability Standards**

Standard	Description	Result
AS1530/Pt.3	Determination of ignitability, flame spread, Heat evolved and smoke developed.	16/0/0/6
BS5852/Source 5-Mod.	Methods of test for assessment of the ignitability of upholstered seating by smouldering and flaming ignition sources, Source 5.	NI,5 - PASS
CAL 117, Sec.3	Requirements, Test Procedure and Apparatus for Testing the Smolder Resistance of Materials Used in Upholstered Furniture	MEETS
F.A.R. 25.853/App.F/Part I	Federal Aviation Regulations - Airworthiness Standards: Transport Category Airplanes – Vertical Burn test.	MEETS
AS/NZS 3744.3	Assessment of the ignitability of upholstered furniture - Ignition source - Match-flame equivalent (Source 2)	NI - PASS

** These test results alone do not assess the fire hazard of the material or the product made from this material under actual fire conditions.

Grade Description

Premium quality, flame retarded, firm cushioning foam. Incorporating Ultra-Fresh™ for antimicrobial protection.

Typical Applications

Firm seat cushioning, transport and contract seating, commercial furniture. Not recommended for stretching and stapling.

Information current as at Nov 2016

Contact Dunlop Foams

447 Foleys Rd, Deer Park, VIC 3023

Phone: 1800 736 634 or +617 3345 3644 Fax: 1800 736 994

Email: enquires@dunlopfoams.com.au